

強度コンテスト試験結果

班	1			2			3			4		
直径1	99.65	100.25	100.75	100.5	99.8	100	100	99.8	99.75	99.5	100.75	100.3
直径2	99.61	100.2	100.75	100.55	99.7	100.1	100.1	99.65	99.8	99.8	100.75	100.1
最大荷重	41500	41300	42300	44200	41800	43400	42500	44600	41400	45800	45300	43700
平均直径	99.63	100.225	100.75	100.525	99.75	100.05	100.05	99.725	99.775	99.65	100.75	100.2
圧縮強度	52.19	51.33	52.02	54.60	52.45	54.13	53.00	55.99	51.92	57.58	55.71	54.34
平均圧縮強度	51.85			53.73			53.64			55.88		
変動係数	1.13			2.67			5.47			3.28		
順位	3			7			13			10		

順位	班	順位	班
1	15	10	4
2	11	11	13
3	1	12	7
4	6	13	3
5	14	14	10
6	5	15	9
7	2	16	8
8	12	17	16
9	17		

班	5			6			7			8		
直径1	100	100.5	100	100	100	100	100.2	100.9	99.9	99.6	100	99.4
直径2	100.1	100.5	100	100.1	100.5	100	99.8	100	99.8	100	99.5	101
最大荷重	34600	34550	35100	34600	35400	34400	35000	37000	37300	39300	33200	35100
平均直径	100.05	100.5	100	100.05	100.25	100	100	100.45	99.85	99.8	99.75	100.2
圧縮強度	43.15	42.70	43.82	43.15	43.97	42.95	43.69	45.78	46.71	49.25926	41.65515	43.64436
平均圧縮強度	43.23			43.36			45.39			44.85292194		
変動係数	1.83			1.73			3.71			9.500514102		
順位	6			4			12			16		

班	9			10			11			12		
直径1	99.5	99.6	100.2	99.3	100.3	99.5	100.1	99.5	99.9	99.7	99.85	99.4
直径2	101.1	100	100.5	99.4	100	100.2	100.05	99.7	100	100.9	99.9	100.15
最大荷重	34000	34450	31450	28100	28400	30400	33700	32940	33500	30300	31400	31500
平均直径	100.3	99.8	100.35	99.35	100.15	99.85	100.075	99.6	99.95	100.3	99.875	99.775
圧縮強度	42.19	43.18	38.99	35.54	35.35	38.07	42.01	41.45	41.86	37.60081	39.29818	39.5024
平均圧縮強度	41.45			36.32			41.77510774			38.80046466		
変動係数	7.33			5.64			0.86			2.85		
順位	15			14			2			8		

班	13			14			15			16			17		
直径1	100.2	99.85	99.9	100.5	99.75	100.1	99.3	100.2	100.25	99.7	99.75	99.9	100	99.8	99.85
直径2	100	99.8	99.9	100.5	100.1	100.15	99.75	100.3	100	99.65	100.15	100	100.75	99.9	99.95
最大荷重	28800	29900	30600	31400	31200	32000	30300	31000	30700	29400	26600	24900	30300	29600	30900
平均直径	100.1	99.825	99.9	100.5	99.925	100.13	99.525	100.25	100.13	99.675	99.95	99.95	100.375	99.85	99.9
圧縮強度	35.88	37.46	38.28	38.81	39.01	39.85	38.19	38.51	38.23	36.94292	33.24088	31.11646	37.54464	37.06397	38.65306
平均圧縮強度	37.21			39.22			38.31			33.77			37.75		
変動係数	3.60			1.79			0.59			9.67			3.02		
順位	11			5			1			17			9		